

Manifattura Pri.Ma.Tex S.r.l.

Sede Legale ed Uffici: Via Tourcoing, 21 59100 Prato – Tel +39 0574 634281
fax +39 0574 635407 codice fiscale e partita IVA 02202530487 www.primatex.it

FICHA TECNICA / Technical sheet

Articulo Article	Flexible TEK Isolante
Composición Composition	100% PL
Altura Width	150 cms ± 3%
Peso Weight	3150 gr/sqm ± 3% 4725 gr/mts ± 3%

Origen de la mercancía Origin of the goods	Italy
Longitud del Rollo Rolls length	10 mts
Espesor Thickness	3,4 mm ± 4%
Costrucción Fabric construction	2 extractos 2 layers

Norma Norm	Descrizione Description	Unidad de Medida Unit of measure	Risultato Result
EN ISO 20344:2012	Absorción del agua	mg/cm ²	88 ± 5%
EN ISO 20344:2012	Desabsorción del agua	%	100 ± 5%
EN ISO 20344:2012	Resistencia eléctrica	Ohm in ambiente secco Ohm in ambiente humedo	> 1 Giga Ohm > 1 Giga Ohm
	Electrical resistance	Ohm in dry atmosphere Ohm in wet atmosphere	> 1 Giga Ohm > 1 Giga Ohm